



FoamTek

A Polymer-modified, Cementitious Adhesive and Base Coat



Coverage

FoamTek 60, 30, and 20:

Approximately 90ft² (8.4m²)

FoamTek 16/20:

Approximately 60ft² (5.6m²)

Coverage will vary depending on ambient temperature, surface temperature, surface porosity, and/or application methods.

Packaging

Moisture resistive, 50lb (22.68kg) bags

Storage

1. Store bags in a cool, dry location.
2. Store away from direct contact with the ground and/or concrete.
3. Store out of direct sunlight.
4. Protect bags from weather and other damage.

Shelf Life

1 year

Color

Natural grey color

Product Description

FoamTek is a dry blend, polymer-modified, portland cement-based material specifically formulated for coating and attaching architectural EPS foam shapes to approved substrates. It is available in FoamTek 60 (fine), FoamTek 30 (medium), FoamTek 20 (med-coarse), or FoamTek 16 (coarse).

Features

Benefits

<i>Dry Mix</i>	Easy to mix and store; minimal waste
<i>Excellent Workability</i>	Easy and quick to apply
<i>Multiple Formulations</i>	Provides suitable base for various finishes
<i>Economical</i>	Reduced material costs

Basic Uses

FoamTek is a base coat and adhesive for attaching and coating architectural foam shapes in residential and commercial applications. It is an excellent material for automated foam coating machines. FoamTek may be used as a leveling coat over approved substrates.

NOTE: Not for use with EIF Systems.

Area of Use

As an adhesive to attach architectural foam shapes to the following substrates:

1. Cement backer board
2. Masonry
3. Poured-in-place and/or tilt-up concrete
4. One coat stucco
5. Brown coat
6. Exterior stucco

As a leveling/skim coat and patching material over:

1. One coat stucco
2. Brown coat
3. Masonry
4. Poured-in-place and/or tilt-up concrete

As a base coat over:

1. EPS architectural foam shapes

Surface Preparation

All surfaces to receive application must be clean and free of debris, dirt, dust, efflorescence, grease, oils, curing agents, and cleaning solutions. Ensure that all surfaces are smooth and free of any irregularities. Repair all cracks with the appropriate patching material for the existing substrate.

Mixing

1. Add 3qt (2.8L) of clean, potable water to an empty, 5 gallon pail.
2. Add one bag of FoamTek to the water while mixing with a Jiffler-type mixer.
3. Mix for a minimum of 3 minutes.
4. Stop mixing and allow the material to set for 5 minutes.
5. Retemper the material, adding only enough water to reach the desired consistency.

NOTE: FoamTek may also be mixed in a paddle type, plaster mixer following the above instructions.

Application

For Use as a Base Coat - Hand Application Method

1. Using a hawk and trowel apply the FoamTek to the receiving surface to a thickness no greater than 1/4" (6.4mm) in a single application.
2. Refer to the Reinforcing Mesh Product Data Sheet for mesh application procedures. (See Note 3)
3. If desired, apply a second coat of material over the first.
4. Float the FoamTek to provide a mechanical key for the finish.

For Use as a Base Coat - Machine Sprayed Method

1. Add the desired amount of mixed material to the sprayer tank.
2. Apply the material to the receiving surface. Avoid puddling.
3. Refer to the Reinforcing Mesh Product Data Sheet for mesh application procedures. (See Note 3)
4. Apply a second coat of material over that of the first.
5. Rod or screed the second coat to a maximum thickness of 1/4" (6.4mm).
6. Float the FoamTek to provide a mechanical key for the finish.

For Use as an Adhesive

1. Apply the FoamTek to the back of the architectural foam shape with an approved notched trowel.
2. Apply the FoamTek side of the architectural foam shape to the substrate.
3. Ensure that the entire architectural foam shape has been firmly attached to the substrate.

For Use as a Leveling or Patching Coat

1. Apply the material to the properly prepared approved substrate. Do not exceed 1/4" thickness in one pass. A second coat can be applied after the first coat has reached its initial cure.
2. Application method will vary due to job conditions.

NOTES

1. Allow FoamTek to set for a minimum of 24-hours prior to working on foam shape.
2. Omega recommends that Acrylic Bonder (AkroLoc) be added to ColorTek prior to application over FoamTek.

3. The use of fiberglass fabric mesh is at the discretion of the architect/builder/contractor. Using mesh will increase impact resistance and may be necessary to properly gauge minimum thickness of the FoamTek. Mesh is always recommended in areas of high traffic. A minimum 3/16" (4.8mm) thickness of FoamTek is required when mesh is not used.

Curing

Curing and/or drying time may vary due to climatic conditions, but should not take less than 24 hours at an ambient and surface temperature of 70°F (21°C) and 55% R.H. Variations in ambient and surface temperature and humidity may prolong curing and/or drying time. All freshly applied material must be protected by an approved protective system from inclement weather until fully dry and cured. It is the responsibility of the applicator to determine if the product is fully cured and/or dry prior to exposing it to rain, snow, dew, and/or any other inclement weather condition that may be detrimental to the product.

Limitations

DO NOT apply product when the ambient and surface temperature is below 40°F (4°C). When hot, dry, or windy conditions exist, protection must be provided. The ambient and surface temperature must maintain the above requirements until fully cured (See CURING). Material that is allowed to freeze may suffer irreparable damage. Protect all work from inclement weather with an approved protective system until fully cured.

DO NOT add any other materials to the mixture of the product without written approval from Omega Products International, Inc.

DO NOT deviate in the mixing or application procedures contained in this, or any other Product Data Sheets, without written approval from Omega Products International, Inc.

DO NOT apply FoamTek if there are contaminants on the receiving surface. Contaminates may include, but are not limited to, dust, debris, efflorescence, and/or oils.

DO NOT add any more water than prescribed.

DO NOT saturate the wall during preparation and/or water curing.

DO NOT leave FoamTek unfinished.

DO NOT use FoamTek as a base coat or an adhesive in EIFS applications.

NOTE: Failure to follow manufacturer's written specifications could result in the following, but not limited to spalling, cracking, peeling, chipping, delamination, discoloration, wash off, and overall system failure.

Cleaning

Cleaning may be accomplished with water immediately after use.

Safety

Avoid contact with eyes or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush immediately with running water for at least 15 minutes. Consult a physician immediately. Do not take internally. Be sure to provide adequate ventilation in enclosed areas. Use of an approved respirator is recommended.

KEEP OUT OF REACH OF CHILDREN

www.omega-products.com

Disclaimer

Omega Products International, Inc. [Manufacturer] MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT(S) SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that the buyer's sole and exclusive remedy for any claimed defective product against Manufacturer shall be the replacement of products actually proven to be defective. Handling and use of the products are beyond

the control of Manufacturer; therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the product. Before applying the product, the user shall determine the suitability of the product for his/her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.

Claims

Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for the alleged defect. For any claim that is not valid Claimant agrees to pay Omega's reasonable charges, including travel and labor associated with investigation of such claim.

Technical Assistance

Technical assistance and information is available by calling Omega Products International, Inc. at (800) 600-6634 or FAX (951) 520-2594 or by e-mail at info@omega-products.com.

Warranty

The following is made in lieu of all expressed and implied rights, warranties and conditions, statutory or otherwise. The manufacturer's only obligation shall be to replace such quantity of products proven to be defective within one year following the date of manufacture, provided that the alleged defective product is returned prepaid to the manufacturer's plant and is accompanied with proof of purchase and batch number.